



®HEBI HIGER CHEMICAL TECHNOLOGY CO., LTD.

ADD: JIJASHAN INDUSTRIAL PARK, HEBI CITY, HENAN PROVINCE, CHINA.

TEL: +86-392-3296888

WEB: www.chemresin.com

FAX: +86-392-2566666

EMAIL: higer@chemresin.com

## Macroporous Weak Acid Cation Resin D113SC

This macroporous cation exchange resin is acrylic acid copolymer cross linked with carboxyl[-COOH]. It is mainly used for double-layer bed, water softening and dealkalization.

### Characteristics

Item	D113SC
Appearance	Milky white or light yellow beads
Matrix	Polyacrylate Macroporous
Ionic Form	H <sup>+</sup>
Mass total exchange capacity mmol/g(dry)	≥ 10.80
Volume total exchange capacity mmol/ml	≥ 4.40
Moisture content %	45.00 - 52.00
Bulk density g/ml	0.72 - 0.80
Specific density g/ml	1.14 - 1.20
Particle size %	(0.315-0.63mm) ≥ 95.0 -
Whole Beads Rate %	≥ 95.0
Uniformity coefficient	≤ 1.4

### Packing:

- Woven bags lined with plastic sheets 25L/bag
- PE valve bags 25L/bag
- Supersacks 1000L/bag

### Storage:

The recommended storage temperature is 5-40°C.  
Prohibited exposure, dehydration, contamination.